

SABIC® PPCOMPOUND 5020

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

SABIC® PPcompound 5020 is a modified Polypropylene which combines high impact, good stiffness and high flow. This material is available in natural and colored form for use in automotive interior applications.

SABIC® PPcompound 5020 is a designated automotive grade.

IMDS ID: 229129721

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|--------|--------------|
| POLYMER PROPERTIES | | | |
| Melt flow rate (MFR) | | | |
| at 230 °C and 2.16 kg | 25 | dg/min | ISO 1133 |
| Density ⁽¹⁾ | 905 | kg/m³ | ISO 1183 |
| Filler content | 0 | % | SABIC method |
| Mould shrinkage ⁽²⁾ | | | |
| 24 hours after injection moulding | 1.4 | % | SABIC method |
| MECHANICAL PROPERTIES ⁽¹⁾ | | | |
| Tensile test | | | |
| Tensile modulus | 1000 | MPa | ISO 527/1A |
| stress at yield | 19 | MPa | ISO 527/1A |
| stress at break | 14 | MPa | ISO 527/1A |
| strain at break | 40 | % | ISO 527/1A |
| Flexural test | | | |
| Flexural modulus | 1050 | MPa | ISO 178/1A |
| Izod impact notched ⁽³⁾ | | | |
| at 23 °C | 45 | kJ/m² | ISO 180/1A |
| at -20 °C | 7 | kJ/m² | ISO 180/1A |
| THERMAL PROPERTIES ⁽¹⁾ | | | |
| Heat deflection temperature | | | |
| at 0.45 MPa (IHT/B) | 85 | °C | ISO 75 |
| Coeff. of linear thermal expansion | | | |
| -30 °C to 100 °C | 118 | µm/mK | ISO 11359-2 |

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.