



# SABIC<sup>®</sup> PPCOMPOUND 7716

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

## DESCRIPTION

SABIC<sup>®</sup> PPcompound 7716 is a mineral filled modified polypropylene. This material combines high scratch resistance with a high stiffness, medium impact and good flow. This material has a broad processing window combined with good esthetical performance and excellent UV exterior stabilization. Typical applications include esthetical automotive exterior trim such as lateral trims, window trims.

SABIC<sup>®</sup> PPcompound 7716 is a designated automotive grade.

IMDS ID: 55028488

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt flow rate (MFR)</b>			
at 230 °C and 2.16 kg	26	dg/min	ISO 1133
<b>Density <sup>(1)</sup></b>	1000	kg/m <sup>3</sup>	ISO 1183
<b>Filler content</b>	16	%	SABIC method
<b>Mould shrinkage <sup>(2)</sup></b>			
24 hours after injection moulding	1.0	%	SABIC method
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile test</b>			
Tensile modulus	1500	MPa	ISO 527/1A
stress at yield	23	MPa	ISO 527/1A
stress at break	17	MPa	ISO 527/1A
strain at break	60	%	ISO 527/1A
<b>Flexural test</b>			
Flexural modulus	1600	MPa	ISO 178/1A
<b>Izod impact notched <sup>(3)</sup></b>			
at 23 °C	8	kJ/m <sup>2</sup>	ISO 180/1A
at 0 °C	5	kJ/m <sup>2</sup>	ISO 180/1A
at -20 °C	3	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL PROPERTIES <sup>(1)</sup></b>			
<b>Heat deflection temperature</b>			
at 0.45 MPa (HDT/B)	110	°C	ISO 75
<b>Coeff. of linear thermal expansion</b>			
-30 °C to 100 °C	85	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

## QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.