



SABIC[®] PPCOMPOUND 7890A

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

SABIC[®] PPcompound 7890A is a mineral filled modified polypropylene. This material combines a very high flow with a good scratch resistance, anti static properties, low density and a good stiffness. This material has a very broad processing window and good esthetical performance. Typical applications include esthetical automotive interior parts such as door panels and interior trim.

SABIC[®] PPcompound 7890A is a designated automotive grade.

IMDS ID: 176098012

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--------------------------------------|----------------|-------------------|--------------|
| POLYMER PROPERTIES | | | |
| Melt flow rate (MFR) | | | |
| at 230 °C and 2.16 kg | 25 | dg/min | ISO 1133 |
| Density ⁽¹⁾ | 960 | kg/m ³ | ISO 1183 |
| Filler content | 10 | % | SABIC method |
| Mould shrinkage ⁽²⁾ | | | |
| 24 hours after injection moulding | 1.0 | % | SABIC method |
| MECHANICAL PROPERTIES ⁽¹⁾ | | | |
| Tensile test | | | |
| Tensile modulus | 1700 | MPa | ISO 527/1A |
| stress at yield | 24 | MPa | ISO 527/1A |
| stress at break | 18 | MPa | ISO 527/1A |
| strain at break | 20 | % | ISO 527/1A |
| Flexural test | | | |
| Flexural modulus | 1800 | MPa | ISO 178/1A |
| Izod impact notched ⁽³⁾ | | | |
| at 23 °C | 7 | kJ/m² | ISO 180/1A |
| at 0 °C | 5 | kJ/m² | ISO 180/1A |
| at -20 °C | 4 | kJ/m² | ISO 180/1A |
| THERMAL PROPERTIES (1) | | | |
| Heat deflection temperature | | | |
| at 0.45 MPa (HDT/B) | 105 | °C | ISO 75 |
| Coeff. of linear thermal expansion | | | |
| -30 °C to 100 °C | 95 | µm/mK | ISO 11359-2 |

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.