



SABIC[®] PPCOMPOUND 8950

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

SABIC[®] PPcompound 8950 is a modified mineral filled Polypropylene for painted automotive exterior applications. The material has a very high stiffness and good dimensional stability whilst maintaining a good impact and flow performance.

SABIC[®] PPcompound 8950 is a designated automotive grade.

IMDS ID: 16487851

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt flow rate (MFR)			
at 230 °C and 2.16 kg	15	dg/min	ISO 1133
Density ⁽¹⁾	1135	kg/m ³	ISO 1183
Filler content	30	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.6	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile			
Tensile modulus	2650	MPa	ISO 527/1A
stress at yield	-	MPa	ISO 527/1A
stress at break	-	MPa	ISO 527/1A
strain at break	-	%	ISO 527/1A
Flexural test			
Flexural modulus	2650	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	20	kJ/m ²	ISO 180/1A
at 0 °C	10	kJ/m ²	ISO 180/1A
at -20 °C	2.5	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	-	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	50	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.