+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# SABIC® PPCOMPOUND G1120U

PP SHORT GLASS FIBER REINFORCED

## **DESCRIPTION**

SABIC<sup>®</sup> PPcompound G1120U is a 20% short glass fiber reinforced and UV stabilized Polypropylene. The base material is a PP homopolymer optimized for good creep resistance. The glass fibres are hydrolytically stable and are chemically coupled to the PP matrix.

#### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	3	dg/min	ISO 1133
Density <sup>(1)</sup>	1040	kg/m³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage <sup>(2)</sup>			
24 hours after injection moulding	0.69	%	SABIC method
MECHANICAL PROPERTIES (1)			
Tensile test			
Tensile modulus	4500	MPa	ISO 527/1A
stress at break	80	MPa	ISO 527/1A
strain at break	3.7	%	ISO 527/1A
Flexural test			
Flexural modulus	4330	MPa	ISO 178/1A
Charpy Impact Strength Notched			
at 23 °C	11	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES (1)			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	145	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	52	μm/mK	ISO 11359-2

<sup>(1)</sup> Injection molded sample ISO527-1A

# **QUALITY**

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.

### STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

<sup>(2)</sup> Injection molded plaque 65x65x3.2mm