+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



SABIC® PPCOMPOUND G3240A

PP SHORT GLASS FIBER REINFORCED

DESCRIPTION

 $SABIC^{\$}$ PPcompound G3240A is a 40% short glass fiber reinforced Polypropylene for under-the-hood and structural applications. The base material is a PP homopolymer and is available in standard black. The glass fibres are chemically coupled to the PP matrix

SABIC[®] PPcompound G3240A is a designated automotive grade.

IMDS ID: 139448304

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230 °C and 2.16 kg	5	dg/min	ISO 1133
Density ⁽¹⁾	1220	kg/m³	ISO 1183
Filler content	40	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	0.6	%	SABIC method
MECHANICAL PROPERTIES (1)			
Tensile test			
Tensile modulus	8900	MPa	ISO 527/1A
stress at break	110	MPa	ISO 527/1A
stress at strain	2.9	%	ISO 527/1A
Flexural test			
Flexural modulus	8900	MPa	ISO 178/1A
Charpy Impact Strength Notched			
at 23 °C	10	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES (1)			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	153	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	42	µm/mK	ISO 11359-2

⁽¹⁾ Injection molded sample ISO527-1A

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO9001.

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

⁽²⁾ Injection molded plaque 65x65x3.2mm