



SABIC[®] STAMAX[™] 30YK270EE

PP LGF REINFORCED IMPACT MODIFIED

DESCRIPTION

SABIC[®] STAMAX 30YK270EE is a 30% long glass fiber reinforced low emission grade with improved impact and flow properties. The glass fibers are chemically coupled to the PP matrix, resulting in high stiffness and strength.

IMDS ID: 80929807

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	1120	kg/m ³	ISO 1183
Glass fibre content	30	%	ISO 3451
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile modulus			
at 23 °C	6200	MPa	ISO 527/1A
at 80 °C	4400	MPa	ISO 527/1A
Tensile strength			
at 23 °C	100	MPa	ISO 527/1A
at 80 °C	55	MPa	ISO 527/1A
Tensile elongation at break			
at 23 °C	2.4	%	ISO 527/1A
Flexural Modulus			
at 23 °C	6000	MPa	ISO 178
at 80 °C	4000	MPa	ISO 178
Flexural strength			
at 23 °C	150	MPa	ISO 178
at 80 °C	75	MPa	ISO 178
Charpy Impact Strength Notched			
at 23 °C	28	kJ/m ²	ISO 179/1eA
at -30 °C	28	kJ/m ²	ISO 179/1eA
Charpy impact unnotched			
at 23 °C	60	kJ/m ²	ISO 179/1eU
at -30 °C	75	kJ/m ²	ISO 179/1eU
THERMAL PROPERTIES			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	158	°C	ISO 75/A
Coeff. of linear thermal expansion			
-30 °C to 100 °C	40	µm/mK	ISO 11359-2

(1) All measurements on injection molded samples.