



SABIC® STAMAX™ 30YM240

PP LGF REINFORCED

DESCRIPTION

SABIC® STAMAX 30YM240 is a 30% long glass fiber reinforced grade. The glass fibres are chemically coupled to the PP matrix, resulting in high stiffness and strength.

IMDS ID: 16496906

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Density	1120	kg/m ³	ISO 1183
Glass fibre content	30	%	ISO 3451
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile modulus			
at 23 °C	6600	MPa	ISO 527/1A
at 80 °C	4500	MPa	ISO 527/1A
Tensile strength			
at 23 °C	105	MPa	ISO 527/1A
at 80 °C	60	MPa	ISO 527/1A
Tensile elongation at break			
at 23 °C	2.3	%	ISO 527/1A
Flexural Modulus			
at 23 °C	6400	MPa	ISO 178
at 80 °C	4600	MPa	ISO 178
Flexural strength			
at 23 °C	160	MPa	ISO 178
at 80 °C	95	MPa	ISO 178
Charpy Impact Strength Notched			
at 23 °C	20	kJ/m ²	ISO 179/1eA
at -30 °C	27	kJ/m ²	ISO 179/1eA
Charpy impact unnotched			
at 23 °C	60	kJ/m ²	ISO 179/1eU
at -30 °C	40	kJ/m ²	ISO 179/1eU
THERMAL PROPERTIES			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	158	°C	ISO 75/A
Coeff. of linear thermal expansion			
-30 °C to 100 °C	44	µm/mK	ISO 11359-2

(1) All measurements on injection molded samples.