



组件 - 塑料
UL 档案号: E45329

SABIC INNOVATIVE PLASTICS B V
EUROPE - RESIN, PLASTICSLAAN 1, BERGEN OP ZOOM 4612 PX NL



Thermocomp: UX06032

Polyphthalamide (PPA), pellets, glass reinforced

NOTE - Material designation may be followed by a color nomenclature consisting of either an alpha/numeric or a numeric/alpha combination.

可燃性	值	测试方法
UL 阻燃等级		UL 94
0.410 mm, ALL	V-0	IEC 60695-11-10, -20
0.450 mm, ALL	V-0	
0.800 mm, ALL	V-0	
1.60 mm, ALL	V-0	
3.00 mm, ALL	V-0	
灼热丝易燃指数		IEC 60695-2-12
0.800 mm	960 °C	
1.60 mm	960 °C	
3.00 mm	960 °C	
热灯丝点火温度		IEC 60695-2-13
0.800 mm	825 °C	
1.60 mm	825 °C	
3.00 mm	850 °C	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
0.410 mm	PLC 0	
0.450 mm	PLC 0	
0.800 mm	PLC 0	
1.60 mm	PLC 0	
3.00 mm	PLC 0	
高电弧燃烧指数(HAI)		UL 746
0.410 mm	PLC 0	
0.450 mm	PLC 0	
0.800 mm	PLC 0	
1.60 mm	PLC 0	
3.00 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 0	UL 746
漏电起痕指数 (3.00 mm)	600 V	IEC 60112
热性能	值	测试方法
RTI Elec		UL 746
0.410 mm	50.0 °C	
0.450 mm	50.0 °C	
0.800 mm	140 °C	
1.60 mm	140 °C	
3.00 mm	140 °C	



组件 - 塑料
UL 档案号: E45329

热性能	值	测试方法
RTI Imp		UL 746
0.410 mm	50.0 °C	
0.450 mm	50.0 °C	
0.800 mm	125 °C	
1.60 mm	125 °C	
3.00 mm	140 °C	
RTI		UL 746
0.410 mm	50.0 °C	
0.450 mm	50.0 °C	
0.800 mm	125 °C	
1.60 mm	125 °C	
3.00 mm	140 °C	

Notice of Disclaimer

By accessing this Yellow Card data information sheet and the database from which this information was generated (the “Yellow Card”), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user’s requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.