



NORYL™ Resin PX9406P
Americas: COMMERCIAL

NORYL PX9406P resin is an FR (non-halogenated) grade potentially suitable for a variety of electronics applications. RTI (impact) = 105 C. F1 listed in BK color.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	770	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	560	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	9.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	28500	kgf/cm ²	ASTM D 638
Flexural Stress, yield, 6.4 mm	1160	kgf/cm ²	ASTM D 790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1150	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	28900	kgf/cm ²	ASTM D 790
Flexural Modulus, 6.4 mm	28900	kgf/cm ²	ASTM D 790
Tensile Stress, yield, 50 mm/min	76	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.7	%	ISO 527
Tensile Strain, break, 50 mm/min	9.4	%	ISO 527
Tensile Modulus, 1 mm/min	2730	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	114	MPa	ISO 178
Flexural Modulus, 2 mm/min	2580	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	13	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	6	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	530	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A



NORYL™ Resin PX9406P

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	122	°C	ASTM D 648
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/120	150	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	118	°C	ISO 75/Af
Relative Temp Index, Elec	110	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B
Relative Temp Index, Mech w/o impact	110	°C	UL 746B
PHYSICAL			
Specific Gravity	1.1	-	ASTM D 792
Melt Volume Rate, MVR at 280°C/5.0 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL			
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index	250	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	0.75	mm	UL 94 by SABIC-IP
UL Compliant, 94-5VA Rating (3)(4)	2.5	mm	UL 94 by SABIC-IP
UL Compliant, 94-5VB Rating (3)(4)	2	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 960°C, passes at	0.75	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 0.8 mm	750	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	775	°C	IEC 60695-2-13



NORYL™ Resin PX9406P

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	105 - 110	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	275 - 305	°C
Nozzle Temperature	275 - 305	°C
Front - Zone 3 Temperature	265 - 305	°C
Middle - Zone 2 Temperature	255 - 300	°C
Rear - Zone 1 Temperature	245 - 295	°C
Mold Temperature	70 - 100	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 70	%
Vent Depth	0.038 - 0.051	mm