



NORYL™ Resin SE100HX
Americas: COMMERCIAL

Improved productivity and reliability. Nonchlorinated, nonbrominated FR.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	620	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	470	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	21	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	910	kgf/cm ²	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	23900	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	23	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	9	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	322	cm-kgf	ASTM D 3763
Instrumented Impact Energy @ peak, -30	33	cm-kgf	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	103	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	94	°C	ASTM D 648
Relative Temp Index, Elec	95	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	95	°C	UL 746B
PHYSICAL			
Specific Gravity	1.09	-	ASTM D 792
Water Absorption, 24 hours	0.06	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Mold Shrinkage on Tensile Bar, xflow (2) (5)	0.5 - 0.7	%	SABIC Method
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A



NORYL™ Resin SE100HX

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating (3)	1.47	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating (3)	5.99	mm	UL 94
Radiant Panel Listing	YES	-	UL Tested
UV-light, water exposure/immersion	F1	-	UL 746C



NORYL™ Resin SE100HX
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	75 - 80	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	250 - 275	°C
Nozzle Temperature	250 - 275	°C
Front - Zone 3 Temperature	240 - 275	°C
Middle - Zone 2 Temperature	225 - 270	°C
Rear - Zone 1 Temperature	215 - 265	°C
Mold Temperature	55 - 75	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 70	%
Vent Depth	0.038 - 0.051	mm