



NORYL GTX™ Resin GTX810

Americas: COMMERCIAL

10% Glass Reinforced PPE+PA Alloy.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Nominal Stress, yld, Type I, 5 mm/min	910	kgf/cm ²	ASTM D 638
Nominal Stress, brk, Type I, 5 mm/min	900	kgf/cm ²	ASTM D 638
Nominal Strain, brk, 5 mm/min	10	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	1580	kgf/cm ²	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	40400	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	119	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	8	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	5	cm-kgf/cm	ASTM D 256
THERMAL			
Vicat Softening Temp, Rate B/50	240	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	245	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	210	°C	ASTM D 648
CTE, -20°C to 150°C, flow	3.96E-05 - 5.04E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.16	-	ASTM D 792
Density	1.162	g/cm ³	ASTM D 792
Water Absorption, 50% RH, equilib	1	%	ASTM D 570
Moisture Absorption, 50% RH, 24 hrs	0.5	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm (5)	0.6 - 0.8	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm (5)	0.65 - 0.85	%	SABIC Method



NORYL GTX™ Resin GTX810

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.47	mm	UL 94



NORYL GTX™ Resin GTX810

Americas: COMMERCIAL

- Do NOT mix NORYL GTX* resin with other grades of NORYL* resins.

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	95 - 105	°C
Drying Time	3 - 4	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.07	%
Minimum Moisture Content	0.02	%
Melt Temperature	280 - 305	°C
Nozzle Temperature	280 - 305	°C
Front - Zone 3 Temperature	275 - 305	°C
Middle - Zone 2 Temperature	270 - 305	°C
Rear - Zone 1 Temperature	265 - 305	°C
Mold Temperature	75 - 120	°C
Back Pressure	0.3 - 1.4	MPa
Screw Speed	20 - 100	rpm
Shot to Cylinder Size	30 - 50	%
Vent Depth	0.013 - 0.038	mm

- Polystyrene and acrylic regrind are effective purging Materials. Use temperature range appropriate for particular purging resin.
- Regrind must also be dried. Maximum 25% regrind.
- Dry at recommended temperatures and times for optimum performance. Overdrying can cause loss of physical properties and/or create appearance defects. Do not exceed recommended basic drying time and temperature above or:
 - 4-8 hrs at 95°C (200°F), 10 hrs max
 - 6-12 hrs at 80°C (175°F), 16 hrs max
 - 8-16 hrs at 65°C (150°F), 24 hrs max
- AVOID air circulating tray ovens. Moisture levels in heated ambient air can exceed moisture level in the resin itself, causing moisture ABSORPTION not drying.
- Avoid melt temperature in excess of 300°C (575°F) and residence times over 6-8 minutes (may affect properties and/or appearance).
- Nozzle temperature controls assist in elimination of drool premature freeze-off.
- Shot sizes in excess of 50% barrel capacity can lead to difficulties in providing a consistent, homogenous plastic melt.