



NORYL™ Resin FP5140HF

Americas: COMMERCIAL

NORYLFP5140HF is an unfilled, injection moldable modified polyphenylene ether resin with an ISO306 Vicat B/120 of 100 deg C. Designed for good dimensional stability and high flow, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V1 UL94 rating at 1.5mm with a specific density of 1.11g/cm³. NORYL FP5140 may be an excellent material for Flat Panel TV enclosure applications requiring good rheological properties, heat resistance, hydrolysis resistance, low density and thin wall flame resistance

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Modulus, 50 mm/min	30000	kgf/cm ²	ASTM D 638
Tensile Stress, yield, 50 mm/min	48	MPa	ISO 527
Tensile Stress, break, 50 mm/min	44	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	2.7	%	ISO 527
Tensile Strain, break, 50 mm/min	21.4	%	ISO 527
Tensile Modulus, 1 mm/min	2530	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2450	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	97	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	78	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.7E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.7E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	97	°C	ISO 306
Vicat Softening Temp, Rate B/120	100	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	80	°C	ISO 75/Af
Relative Temp Index, Elec	65	°C	UL 746B



NORYL™ Resin FP5140HF

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
Relative Temp Index, Mech w/impact	65	°C	UL 746B
Relative Temp Index, Mech w/o impact	65	°C	UL 746B
PHYSICAL			
Specific Gravity	1.11	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Density	1.11	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.18	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Melt Volume Rate, MVR at 280°C/1.2 kg	17	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 280°C/2.16 kg	48	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Compliant, 94V-1 Flame Class Rating (3)(4)	1.5	mm	UL 94 by SABIC-IP



NORYL™ Resin FP5140HF

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	70 - 80	°C
Drying Time	2 - 3	hrs
Melt Temperature	250 - 285	°C
Nozzle Temperature	240 - 270	°C
Front - Zone 3 Temperature	250 - 285	°C
Middle - Zone 2 Temperature	230 - 260	°C
Rear - Zone 1 Temperature	200 - 220	°C
Hopper Temperature	60 - 80	°C
Mold Temperature	40 - 65	°C