



NORYL™ Resin WCD883AU

Asia Pacific: COMMERCIAL

Flexible and non-halogenated flame retardant extrusion grade intended for evaluation in applications such as jacket of HD 21.14 flexible cables. Flame retardant performance capable of meeting EN 50265-2-1 requirement.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 50 mm/min	140	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	260	%	ASTM D 638
Flexural Modulus, 12.5 mm/min, 100 mm span	300	kgf/cm ²	ASTM D 790
Hardness, Shore A, 30S reading	<87	-	ASTM D 2240
Tensile Stress, break, 50 mm/min	15	MPa	ISO 527
Tensile Strain, break, 50 mm/min	235	%	ISO 527
Flexural Modulus, 12.5 mm/min	40	MPa	ISO 178
PHYSICAL			
Specific Gravity	1.17	-	ASTM D 792
Melt Flow Rate, 250°C/10.0 kgf	4	g/10 min	ASTM D 1238
Water Absorption, 23°C/24hrs	0.02	%	ISO 62-1
ELECTRICAL			
Volume Resistivity	5.6E+15	Ohm-cm	ASTM D 257
Surface Resistivity	2.5E+16	Ohm	ASTM D 257
Dielectric Strength in oil, 2.0mm	25	kV/mm	ASTM D 149
Relative Permittivity, 1 GHz	3	-	ASTM D 150
Dissipation Factor, 1 GHz	0.003	-	ASTM D 150
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS			
Smoke Density on 0.5mm plaque, Non-flame, Ds, max	142	-	ASTM E 662
Smoke Density on 0.5mm plaque, Flame, Ds, max	57	-	ASTM E 662
Glow Wire Flammability Index 850°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	36	%	ISO 4589



NORYL™ Resin WCD883AU

Asia Pacific: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
WIRE AND CABLE - UL 1581 tested on 2.0mm wire with 0.12mmx20 stranded copper			
Tensile strength @ break	18	MPa	UL 1581
Tensile elongation @ break	263	%	UL 1581
Tensile strength @ break after 7days @136°C	19	MPa	UL 1581
Tensile elongation @ break after 7days @136°C	243	%	UL 1581
Heat Deformation at 100°C/250g	23	%	UL 1581
Vertical Flame Test	PASSES	-	EN 50265-2-1



NORYL™ Resin WCD883AU

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Wire Coating Extrusion		
Drying Temperature	75 - 85	°C
Drying Time	5 - 7	hrs
Drying Time (Cumulative)	12	hrs
Maximum Moisture Content	0.02	%
Extruder Length/Diameter Ratio (L/D)	22:1 to 26:1	-
Screw Speed	15 - 85	rpm
Feed Zone Temperature	180 - 220	°C
Middle Zone Temperatures	220 - 250	°C
Head Zone Temperature	220 - 250	°C
Neck Temperature	220 - 250	°C
Cross-head Temperature	220 - 250	°C
Die Temperature	220 - 250	°C
Melt Temperature	220 - 250	°C
Conductor Pre-heat Temperature	25 - 120	°C
Screen Pack	150 - 100	-
Cooling Water Air Gap	100 - 200	mm
Water Bath Temperature	15 - 60	°C

• NOTE: Recommended Drying Parameters are based on usage of Dehumidify Drying / Drying Oven.