



LNP™ THERMOCOMP™ Compound ZF006

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound ZF-1006

Product reorder name: ZF006

LNP THERMOCOMP ZF006 is a compound based on PPO resin containing 30% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Flexural Stress, brk, 1.3 mm/min, 50 mm span	1640	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	88000	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	46	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	11	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
PHYSICAL			
Density	1.3	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.3 - 0.5	%	ASTM D 955



LNP™ THERMOCOMP™ Compound ZF006

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120	°C
Drying Time	4	hrs
Melt Temperature	300 - 305	°C
Front - Zone 3 Temperature	300 - 310	°C
Middle - Zone 2 Temperature	290 - 300	°C
Rear - Zone 1 Temperature	275 - 290	°C
Mold Temperature	80 - 110	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm