



LNP™ LUBRICOMP™ Compound OFL38A

Europe-Africa-Middle East: COMMERCIAL

LNP LUBRICOMP OFL38A is a compound based on PPS - Branched resin containing Glass Fiber, PTFE. Added features include : Internally Lubricated.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	147	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	14700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	206	MPa	ISO 178
Flexural Modulus, 2 mm/min	12700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.6E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	3.8E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	280	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	264	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	0.2	%	SABIC Method
Density	1.8	g/cm ³	ISO 1183
ELECTRICAL			
Comparative Tracking Index	175	V	IEC 60112
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	1.7	mm	UL 94
Glow Wire Ignitability Temperature, 1.0 mm	825 - 960	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	875 - 960	°C	IEC 60695-2-13



LNP™ LUBRICOMP™ Compound OFL38A

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Melt Temperature	315 - 320	°C
Front - Zone 3 Temperature	330 - 345	°C
Middle - Zone 2 Temperature	320 - 330	°C
Rear - Zone 1 Temperature	305 - 315	°C
Mold Temperature	140 - 165	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm