



LNP* Lubricomp* Compound O-BG

Asia Pacific: COMMERCIAL

LNP LUBRICOMP* O-BG is a compound based on PPS - Linear resin containing Bearing Grade, Lubricants, Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, break	1610	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	184900	kgf/cm ²	ASTM D 638
Flexural Stress	2500	kgf/cm ²	ASTM D 790
Flexural Modulus	203100	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	49	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	260	°C	ASTM D 648
PHYSICAL			
Density	1.51	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.01 - 0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.4 - 0.6	%	ASTM D 955
Wear Factor Washer	24	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified
Dynamic COF	0.47	-	ASTM D 3702 Modified
Static COF	0.33	-	ASTM D 3702 Modified
ELECTRICAL			
Surface Resistivity	1.E+00 - 1.E+02	Ohm	ASTM D 257



LNP* Lubricomp* Compound O-BG

Asia Pacific: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Melt Temperature	315 - 320	°C
Front - Zone 3 Temperature	330 - 345	°C
Middle - Zone 2 Temperature	320 - 330	°C
Rear - Zone 1 Temperature	305 - 315	°C
Mold Temperature	140 - 165	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm