



LNP™ THERMOCOMP™ Compound OC006

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound OC-1006
Product reorder name: OC006

LNP THERMOCOMP OC006 is a compound based on PPS-Linear resin containing 30% Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1890	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.2	%	ASTM D 638
Tensile Modulus, 50 mm/min	243900	kgf/cm ²	ASTM D 638
Flexural Stress	2880	kgf/cm ²	ASTM D 790
Flexural Modulus	215800	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	65	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	108	°C	ASTM D 648
PHYSICAL			
Density	1.43	g/cm ³	ASTM D 792



LNP™ THERMOCOMP™ Compound OC006

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Melt Temperature	315 - 320	°C
Front - Zone 3 Temperature	330 - 345	°C
Middle - Zone 2 Temperature	320 - 330	°C
Rear - Zone 1 Temperature	305 - 315	°C
Mold Temperature	140 - 165	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm