



LNP™ LUBRICOMP™ Compound CG006

Europe-Africa-Middle East: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound CL4360S NT8

Product reorder name: CG006

LNP* Lubricomp* CG006 is a compound based on Polystyrene resin containing Graphite.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.3	%	ISO 527
Tensile Modulus, 1 mm/min	6200	MPa	ISO 527
Flexural Stress, break, 2 mm/min	72	MPa	ISO 178
Flexural Modulus, 2 mm/min	5400	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	2	kJ/m ²	ISO 180/1A
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	86	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.1 - 0.3	%	SABIC Method
Wear Factor Washer	799	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Instr.
Dynamic COF	0.3	-	ASTM D 3702 Modified: Instr.
Static COF	0.55	-	ASTM D 3702 Modified: Instr.
Density	1.22	g/cm ³	ISO 1183



LNP™ LUBRICOMP™ Compound CG006
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	250	°C
Front - Zone 3 Temperature	265 - 275	°C
Middle - Zone 2 Temperature	245 - 255	°C
Rear - Zone 1 Temperature	220 - 230	°C
Mold Temperature	40 - 65	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm