



LNP™ THERMOCOMP™ Compound GF006XXZ

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound GF-1006

Product reorder name: GF006XXZ

LNP THERMOCOMP™ GF006XXZ is a compound based on Polysulfone resin containing 30% Glass Fiber.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1060	kgf/cm ²	ASTM D 638
Tensile Strain, break	2	%	ASTM D 638
Tensile Modulus, 50 mm/min	89900	kgf/cm ²	ASTM D 638
Flexural Stress	1590	kgf/cm ²	ASTM D 790
Flexural Modulus	84300	kgf/cm ²	ASTM D 790
Tensile Stress, break	100	MPa	ISO 527
Tensile Strain, break	1.9	%	ISO 527
Tensile Modulus, 1 mm/min	8420	MPa	ISO 527
Flexural Stress	150	MPa	ISO 178
Flexural Modulus	8390	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	43	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	6	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	90	cm-kgf	ASTM D 3763
Multiaxial Impact	30	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	27	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	181	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.06E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.6E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	3.66E-05	1/°C	ISO 11359-2



LNP™ THERMOCOMP™ Compound GF006XXZ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	182	°C	ISO 75/Af
PHYSICAL			
Density	1.483	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.2	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.6	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.22	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.58	%	ISO 294
Density	1.47	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.3	%	ISO 62



LNP™ THERMOCOMP™ Compound GF006XXZ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	360 - 370	°C
Front - Zone 3 Temperature	350 - 360	°C
Middle - Zone 2 Temperature	340 - 350	°C
Rear - Zone 1 Temperature	325 - 340	°C
Mold Temperature	150	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm