



CYCOLAC™ Resin INP576

Europe-Africa-Middle East: COMMERCIAL

Can be used as compounding additives for polymer blends. Medium molecular weight SAN. Can be blended with high rubber graft modifier resins to produce customized ABS properties. Suitable for direct weather exposure. Most versatile SAN for balance of processing and physical properties.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	420	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	690	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.2	%	ASTM D 638
Tensile Modulus, 5 mm/min	40500	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	980	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	36400	kgf/cm ²	ASTM D 790
Hardness, Rockwell R	122	-	ASTM D 785
Flexural Stress, yield, 2 mm/min	68	MPa	ISO 178
Flexural Modulus, 2 mm/min	3540	MPa	ISO 178
IMPACT			
Charpy Impact, unnotched, 23°C	1	kJ/m ²	ISO 179/2C
Izod Impact, notched, 23°C	2	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	1	cm-kgf/cm	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	1	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	1	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	98	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	87	°C	ASTM D 648
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	106	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	84	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792



CYCOLAC™ Resin INP576
Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
PHYSICAL			
Melt Flow Rate, 230°C/3.8 kgf	23	g/10 min	ASTM D 1238
Density	1.08	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	78	g/10 min	ISO 1133
OPTICAL			
Yellowness Index	1	-	ASTM D 1925