



SABIC[®] FORTIFY[™] C0570

POLYOLEFIN ELASTOMER

DESCRIPTION

SABIC[®] FORTIFYTM C0570 is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets. SABIC[®] FORTIFYTM C0570 is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow

SABIC FORTIFY C0570 is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow characteristics.

TYPICAL APPLICATIONS

Typical applications are impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------------|----------------|-------------------|--------------|
| POLYMER PROPERTIES | | | |
| Density | 868 | kg/m ³ | ASTM D792 |
| Melt Flow Rate | | | |
| at 190°C and 2.16 kg | 0.5 | g/10 min | ASTM D1238 |
| at 230°C and 2.16 kg | 0.9 | g/10 min | ASTM D1238 |
| Mooney viscosity (ML 1+4, 121 °C) | 36 | MU | ASTM D1646 |
| MECHANICAL PROPERTIES (1) | | | |
| Tensile Properties | | | |
| 100% modulus | 3.1 | MPa | ASTM D638 |
| elongation | 800 | % | ASTM D638 |
| strength at break | 10.3 | MPa | ASTM D638 |
| Durometer Hardness | | | |
| shore A (1 second) | 74 | - | ASTM D2240 |
| shore D (1 second) | 23 | - | ASTM D2240 |
| Flexural Modulus (1% Secant) | 15.2 | MPa | ASTM D790 A |
| Tear Strength (Type C) | 45.1 | kN/m | ASTM D624 |
| THERMAL PROPERTIES | | | |
| Peak Melting Temperature | 59 | °C | SABIC method |
| Glass Transition Temperature, Tg | -54 | °C | SABIC method |

(1)

All physical properties were measured from specimens cut from compression molded. These typical values depend onmanufacturing conditions. Therefore, customers should confirm the product performance by using their own tests.