

SABIC® SUPEER™ 8115

METALLOCENE LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

SABIC® SUPEER™ 8115 is an ethylene-octene copolymer produced via Nexlene™ Technology. It performs well in a wide range of general purpose and high performance LLDPE blown film applications and has good processability. The grade offers better performance in terms of tensile properties, stiffness / toughness ratio and optical properties.

TYPICAL APPLICATIONS

Lamination film, frozen bag, liquid pouch, heavy duty bag, industrial liner, agriculture film, stretch hood, surface protective film.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190°C and 2.16 kg	1.1	g/10 min	ASTM D1238
OPTICAL PROPERTIES			
Haze	10	%	ASTM D1003
FILM PROPERTIES			
Tensile test film ⁽¹⁾			
stress at break, MD	52	MPa	ASTM D882
stress at break, TD	49	MPa	ASTM D882
elongation at break, MD	650	%	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
elongation at break, TD	730	%	ASTM D882
stress at yield, MD	11	MPa	ASTM D882
1% secant modulus, MD	136	MPa	ASTM D882
1% secant modulus, TD	151	MPa	ASTM D882
Dart Impact F50 ⁽¹⁾	>1000	g	ASTM D1709
Elmendorf Tear Strength ⁽¹⁾			
MD	15	g/µm	ASTM D1922
TD	24	g/µm	ASTM D1922
THERMAL PROPERTIES			
Melting Point	~112	°C	SABIC method

(1) Properties have been measured by producing 50 µm film with 2.5 BUR using 100% SUPEER™ 8115.

PROCESSING CONDITIONS

Typical processing conditions for SUPEER™ 8115 are:
Barrel temperature: 180 - 200°C, Blow up ratio: 2.0 - 3.0