

# SUPEERTM MLLDPE 7120BE

METALLOCENE C6 LLDPE

## DESCRIPTION

SUPEERTM 7120BE is a metallocene ethylene-hexene copolymer. It has a good processability for film extrusion via cast technology mainly due to its dedicated stabilization package. This grade is typically used to produce thin stiff stretch film for hand wrap and semi-automatic wrapper applications. Stretch film produced with this grade offers increased holding force, impact and puncture resistance. In silage wrap cast film 7120BE it also increases puncture resistance and shows a limiting neck-in.

Besides this, SUPEERTM 7120BE can typically be used as booster resin for cast and blown stretch film that contain PCR (Post Consumer Recycling) material. Here it will boost mechanical properties, reduce gels during film extrusion and give smooth process ability.

Properties have been measured on cast film of 25 µm.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	1	dg/min	ASTM D1238
Density	920	kg/m³	ASTM D792
<b>FILM PROPERTIES</b>			
Tear strength TD Elmendorf	23	g/µm	ASTM D1922
Tear strength MD Elmendorf	15	g/µm	ASTM D1922
<b>Tensile test film</b>			
Strain at break MD	550	%	ASTM D882
Strain at break TD	650	%	ASTM D882
Stress at break MD	60	MPa	ASTM D882
Stress at break TD	55	MPa	ASTM D882
Yield stress MD	10	MPa	ASTM D882
Yield stress TD	10	MPa	ASTM D882
<b>THERMAL PROPERTIES</b>			
<b>DSC test</b>			
melting point	124	°C	ASTM D3418
<b>Vicat Softening Temperature</b>			
at 10 N (VST/A)	107	°C	ISO 306