

# SUPEERTM MLLDPE 7158LA

METALLOCENE C6 LLDPE  
REGION AMERICAS

## DESCRIPTION

SUPEERTM Metallocene Linear Low Density Polyethylene (mLLDPE) 7158LA is a metallocene ethylene-hexene copolymer. It has a good processability and performs well in a wide range of general purpose and high performance blown film applications. Films produced with this grade offer good tensile and impact strength, puncture resistance and sealing properties. The resin contains anti-block and slip agent. SUPEERTM 7158LA is TNPP free.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

## TYPICAL APPLICATIONS

SUPEERTM Metallocene Linear Low Density Polyethylene (mLLDPE) 7158LA is typically used for applications like heavy duty bags, agriculture film, stretch hood, lamination film, frozen bags.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Melt Flow Rate (MFR)			
at 190 °C and 2.16 kg	1.5	g/10 min	ASTM D1238
Density	918	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
Dart Impact Strength	510	g	ASTM D1709
<b>OPTICAL PROPERTIES</b>			
Gloss (45°)	30	‰	ASTM D2457
Haze	19	%	ASTM D1003
<b>FILM PROPERTIES</b>			
Tensile test film <sup>(1)</sup>			
Stress at break MD	45	MPa	ASTM D882
Stress at break TD	41	MPa	ASTM D882
Strain at break MD	500	%	ASTM D882
Strain at break TD	600	%	ASTM D882
Stress at yield MD	8.7	MPa	ASTM D882
Stress at yield TD	8.8	MPa	ASTM D882
Elmendorf Tear Strength MD	280	g	ASTM D1922
Elmendorf Tear Strength TD	410	g	ASTM D1922
Puncture Force	39	N	SABIC method
Puncture Energy	2.1	J	SABIC method
<b>THERMAL PROPERTIES</b>			
DSC test			
Melting point	120	°C	SABIC method

(1) Properties have been measured on blown film of 25 µm and BUR = 2.5