

# SUPEERTM MLLDPE 8115L

## METALLOCENE LINEAR LOW DENSITY POLYETHYLENE

### DESCRIPTION

SABIC® SUPEERTM 8115L is an ethylene-octene copolymer produced via Nexlene™ Technology. It performs well in a wide range of general purpose and high performance LLDPE blown film applications and has good processability. The grade offers better performance in terms of tensile properties, stiffness / toughness ratio and optical properties.

### TYPICAL APPLICATIONS

Lamination film, frozen bag, liquid pouch, heavy duty bag, industrial liner, agriculture film, stretch hood, surface protective film.

### TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Melt Flow Rate (MFR)	1.1	g/10 min	ASTM D1238
at 190°C and 2.16 kg			
Density	915	kg/m <sup>3</sup>	ASTM D1505
<b>FORMULATION</b>			
Slip agent	✓	-	-
Anti block agent	✓	-	-
<b>OPTICAL PROPERTIES</b>			
Haze	10	%	ASTM D1003
<b>FILM PROPERTIES<sup>(1)</sup></b>			
Tensile test film			
stress at break, TD	49	MPa	ASTM D882
stress at yield, MD	11	MPa	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
stress at break, MD	52	MPa	ASTM D882
elongation at break, MD	650	%	ASTM D882
elongation at break, TD	730	%	ASTM D882
1% secant modulus, MD	136	MPa	ASTM D882
1% secant modulus, TD	151	MPa	ASTM D882
Dart Impact F50	>1000	g	ASTM D1709
Elmendorf Tear Strength			
MD	15	g/μm	ASTM D1922
TD	24	g/μm	ASTM D1922
<b>THERMAL PROPERTIES</b>			
Melting Point	~112	°C	SABIC method

(1) Properties have been measured by producing 50 μm film with 2.5 BUR using 100% SUPEERTM 8115.