

# PLATAMID® M 1757 POWDER

Platamid® M 1757 Powder  
Copolyamide Hot Melt Adhesive / Textile Applications

Platamid® M 1757 Powder is a medium melt viscosity copolyamide adhesive powder for the production of fusible interlinings. Platamid® M 1757 Powder offers excellent laundry resistance up to 60°C and good steam resistance at moderate fusing conditions.

| 性能             | 干 /<br>已调节 | 单位        | 测试标准           |
|----------------|------------|-----------|----------------|
| 流变性能           |            |           |                |
| 熔体体积流动速度       | 25 / *     | cm³/10min | ISO 1133       |
| 温度             | 160 / *    | °C        | -              |
|                | 320 / *    | °F        | -              |
| 载荷             | 2.16 / *   | kg        | -              |
|                | 4.76 / *   | lb        | -              |
| 热性能            |            |           |                |
| 熔融温度, 10°C/min | 109 / *    | °C        | ISO 11357-1/-3 |

## AVAILABLE GRADES

This powder grade is available in different grain sizes:

- Platamid® M 1757 PA 80 (0-80 µm paste dot)
- Platamid® M 1757 PTA 120 (0-120 µm micro powder dot)
- Platamid® M 1757 PTA 170/20 (0-170 µm powder dot)
- Platamid® M 1757 PTA 200 (80-200 µm powder dot)
- Platamid® M 1757 PRA 170 (80-170 µm double dot)
- Platamid® M 1757 PRA 200 (80-200 µm double dot)

## PACKAGING

- Platamid® M 1757 powder is delivered in 20 kg sealed bags.

## SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

|                               |                                                                                                                                                                                                                                                                                   |
|-------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 加工方法                          | Headquarters:<br>Arkema France<br>420 rue d'Estienne d'Orves 92705<br>Colombes Cedex France<br>T +33 (0)1 49 00 80 80<br>arkema.com<br><br>Arkema Inc. – High Performance<br>Polymers<br>900 First Avenue<br>King of Prussia, PA 19406<br>Tel.: +1 610 205 7000<br>hpp.arkema.com |
| Scattering, Paste, Double Dot |                                                                                                                                                                                                                                                                                   |
| 供货形式                          |                                                                                                                                                                                                                                                                                   |
| 粉料                            |                                                                                                                                                                                                                                                                                   |
| 特殊性能                          | Arkema Inc. – High Performance<br>Polymers<br>900 First Avenue<br>King of Prussia, PA 19406<br>Tel.: +1 610 205 7000<br>hpp.arkema.com                                                                                                                                            |
| Adhesive                      |                                                                                                                                                                                                                                                                                   |
| 地区供应                          | Arkema Inc. – High Performance<br>Polymers<br>900 First Avenue<br>King of Prussia, PA 19406<br>Tel.: +1 610 205 7000<br>hpp.arkema.com                                                                                                                                            |
| 北美, 欧洲, 亚太, 中南美洲, 中东/非洲       |                                                                                                                                                                                                                                                                                   |