

PLATAMID® M 2468 PELLETS

Platamid® M 2468

共聚多酰胺热熔胶/挤出应用

Platamid® M 2468

是一种球状颗粒的标准热塑性塑料共聚多酰胺热熔胶。该为低至中等熔融粘度，特别适用于挤出制造网、单丝和复丝以及薄膜。

Platamid® M 2468 能在低熔融条件下与各种极性基材（热塑性塑料、热固性塑料、金属、天然纤维等）形成极好的粘结力。

Platamid® M 2468 具有良好的耐干洗性以及耐水洗性能（高达60°C）。

供货牌号

本产品的供应有：

—含荧光剂的干燥型（M 2468 TA）

—含荧光剂的非干燥型（M 2468 FA）

包装

Platamid® M 2468 TA的供货规格为25公斤密封袋装和500公斤密封大袋装（GRVS）。

Platamid® M 2468 FA的供货规格为500公斤密封硬质容器装（GRVC）和500公斤密封大袋装（GRVS）。

这些可以随时加工处理。

保质期

自发货之日起2年。有关过期使用的任何事宜，请咨询我司技术服务人员。

可再生碳含量>25%

（计算值，ASTM D6866）

性能	干 / 已调节	单位	测试标准
流变性能			
熔体体积流动速度	26 / *	cm³/10min	ISO 1133
温度	160 / *	°C	-
	320 / *	°F	
载荷	2.16 / *	kg	-
	4.76 / *	lb	
热性能			
熔融温度, 10°C/min	102 / *	°C	ISO 11357-1/-3
其它性能			
密度	1060 / -	kg/m³	ISO 1183
	1.06 / -	g/cm³	
%Bio-Based	25	-	ASTM D6866

AVAILABLE GRADES

This product is available:

- Dried with optical brightener (M 2468 TA)
- Un-dried with optical brightener (M 2468 FA)

PACKAGING

- Platamid® M 2468 TA is delivered in 25 kg sealed bags and 500kg sealed big bags (GRVS).
- Platamid® M 2468 FA is delivered in 500kg sealed rigid containers (GRVC) and 500kg sealed big bags (GRVS).

These grades are ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT

>25% (calculated, ASTM D6866)

PLATAMID®

M 2468 PELLETS

加工方法	
薄膜挤出成型, Melt Spinning, Web Processing	
供货形式	
粒料	
特殊性能	
Adhesive, 生物基	
地区供应	
北美, 欧洲, 亚太, 中南美洲, 中东/非洲	