

Technical Data Sheet

Accucomp ABS827L

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Features	• Platable		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 Kg)	1.8 g/10 min	1.8 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	261000 psi	1800 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	7830 psi	54.0 MPa	
Break	5080 psi	35.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	20 %	20 %	
Flexural Modulus	392000 psi	2700 MPa	ASTM D790
Flexural Strength	10900 psi	75.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	5.8 ft·lb/in	310 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	109	109	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	194 °F	90.0 °C	
264 Psi (1.8 Mpa), Unannealed	169 °F	76.0 °C	

Notes

These are typical property values not to be construed as specification limits.