

Technical Data Sheet

# Polyflam RABS 90000 UV5

Acrylonitrile Butadiene Styrene  
 LyondellBasell Industries  
 Engineering Plastics

**Product Description**

Flame retardant ABS standard grade without PBDE and higher thermal stability

**General**

Features	<ul style="list-style-type: none"> <li>Flame Retardant</li> <li>Good Processability</li> </ul>	<ul style="list-style-type: none"> <li>Good Thermal Stability</li> <li>Non-Blooming</li> </ul>
UL File Number	E86615	
Processing Method	Injection Molding	
Part Marking Code (ISO 11469)	ABS FR17	
Resin ID (ISO 1043)	ABS FR17	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 Kg)	30 cm <sup>3</sup> /10min	30 cm <sup>3</sup> /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	319000 psi	2200 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	5800 psi	40.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	3.0 %	3.0 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	2.4 ft·lb/in <sup>2</sup>	5.0 kJ/m <sup>2</sup>	
73°F (23°C)	4.8 ft·lb/in <sup>2</sup>	10 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	21 ft·lb/in <sup>2</sup>	45 kJ/m <sup>2</sup>	
73°F (23°C)	38 ft·lb/in <sup>2</sup>	80 kJ/m <sup>2</sup>	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Ball Indentation Hardness	16400 psi	113 MPa	ISO 2039-1
---------------------------	-----------	---------	------------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	198 °F	92.0 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	176 °F	80.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	205 °F	96.0 °C	ISO 306/B50
--	221 °F	105 °C	ISO 306/A50
Ball Pressure Test (194°F (90°C))	Pass	Pass	IEC 60695-10-2
RTI Elec			UL 746B
0.06 In (1.5 Mm)	140 °F	60.0 °C	
0.12 In (3.0 Mm)	140 °F	60.0 °C	
RTI Imp			UL 746B
0.06 In (1.5 Mm)	140 °F	60.0 °C	
0.12 In (3.0 Mm)	140 °F	60.0 °C	
RTI Str			UL 746B
0.06 In (1.5 Mm)	140 °F	60.0 °C	
0.12 In (3.0 Mm)	140 °F	60.0 °C	

Technical Data Sheet

# Polyflam RABS 90000 UV5

Acrylonitrile Butadiene Styrene

LyondellBasell Industries

Engineering Plastics

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	475 V	475 V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.06 In (1.5 Mm)	PLC 3	PLC 3	
0.12 In (3.0 Mm)	PLC 3	PLC 3	
Hot-wire Ignition (HWI)			UL 746A
0.06 In (1.5 Mm)	PLC 3	PLC 3	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
Flame Rating			UL 94 IEC 60695-11-10, -20
0.06 In (1.5 Mm)	V-0	V-0	
0.12 In (3.0 Mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1340 °F	725 °C	
0.12 In (3.0 Mm)	1340 °F	725 °C	
Oxygen Index	28 %	28 %	ISO 4589-2

Technical Data Sheet

**Polyflam RABS 90000 UV5**

Acrylonitrile Butadiene Styrene  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	428 to 464 °F	220 to 240 °C
Mold Temperature	104 to 140 °F	40 to 60 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Screw Speed	< 709 in/min	< 18 m/min

**Injection Notes**

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

**Notes**

These are typical property values not to be construed as specification limits.