

Technical Data Sheet

Polyman ABS M/Hi A BLK70400

Acrylonitrile Butadiene Styrene

Product Description

increased impact modified ABS-standard with antistatic behaviour

Processing Method	Injection Molding
Attribute	Impact Modified
Additive	Antistatic; Impact Modifier

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	15	cm ³ /10 min	ISO 1133
Density, (Method A)	1.05	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	48.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	2.1	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2200	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	20	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	9.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	71	kJ/m ²	ISO 179
Notched Izod Impact (Area), (23 °C)	25.0	kJ/m ²	ASTM D256
Hardness			
Ball Indentation Hardness, (H 358/30)	110	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	94.0	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	95.0	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	91.0	°C	ISO 75-2/A
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	600	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Glow Wire Flammability Index, (2.0 mm)	550	°C	IEC 60695-2-12
Additional Information			
Water Absorption 23C/50RH	1.2	%	ISO 62
UL Information			
Flammability Classification, (1.5 mm)	HB		IEC 60695-11-10, -20