

## Technical Data Sheet

**Polyman ABS M/MI GLA YEW 21682**

Acrylonitrile Butadiene Styrene

**Product Description**

ABS grade with increased impact strength, high gloss and antistatic agent

<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Impact Resistance; High Gloss
<b>Additive</b>	Antistatic

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Volume Flow Rate, (220 °C/10.0 kg)	30	cm <sup>3</sup> /10 min	ISO 1133
Density, (Method A)	1.05	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	43.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	2.3	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2300	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	15	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	No Break		ISO 179
Notched Izod Impact (Area), (23 °C)	13.0	kJ/m <sup>2</sup>	ASTM D256
<b>Hardness</b>			
Ball Indentation Hardness, (H 358/30)	96.0	MPa	ISO 2039-1
<b>Thermal</b>			
Vicat Softening Temperature, (B (50N), 50 °C/h)	95.0	°C	ISO 306
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	90.0	°C	ISO 75-2/A
<b>Electrical</b>			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Surface Resistivity	>1.0E+15	ohm	IEC 60093
<b>UL Information</b>			
Flammability Classification, (1.5 mm)	HB		IEC 60695-11-10, -20