

Technical Data Sheet

# RONFALIN<sup>®</sup> ABS 1336 CA

Acrylonitrile Butadiene Styrene  
Engineering Plastics

**Product Description**

General purpose ABS Compound, good flow, constant antistatic.

**General**

Processing Method • Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.05 g/cm <sup>3</sup>	1.05 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	32 cm <sup>3</sup> /10min	32 cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	290000 psi	2000 MPa	ISO 527-2/1A/1
Tensile Stress			ISO 527-2/1A/50
Yield	6090 psi	42.0 MPa	
Break	4060 psi	28.0 MPa	
Tensile Strain (Yield)	3.4 %	3.4 %	ISO 527-2/1A/50
Nominal Tensile Strain at Break	16 %	16 %	ISO 527-2/1A/50
Flexural Modulus <sup>1</sup>	319000 psi	2200 MPa	ISO 178
Flexural Stress <sup>1</sup> (4.7% Strain)	9570 psi	66.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.8 ft·lb/in <sup>2</sup>	8.0 kJ/m <sup>2</sup>	
73°F (23°C)	8.1 ft·lb/in <sup>2</sup>	17 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	12900 psi	89.0 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	194 °F	90.0 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	172 °F	78.0 °C	ISO 75-2/af
Vicat Softening Temperature			
--	219 °F	104 °C	ISO 306/A50
--	207 °F	97.0 °C	ISO 306/B50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+11 ohms	1.0E+11 ohms	IEC 60093
Volume Resistivity	1.0E+13 ohms·m	1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112

Technical Data Sheet

# RONFALIN<sup>®</sup> ABS 1336 CA

Acrylonitrile Butadiene Styrene  
Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.6 mm)	HB	HB	
0.13 in (3.2 mm)	HB	HB	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1290 °F	700 °C	
0.12 in (3.0 mm)	1290 °F	700 °C	

### Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

**RONFALIN<sup>®</sup> ABS 1336 CA**

Acrylonitrile Butadiene Styrene  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Regrind	30 %	30 %
Processing (Melt) Temp	446 to 482 °F	230 to 250 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

**Notes**

<sup>1</sup> 0.079 in/min (2.0 mm/min)

**Notes**

These are typical property values not to be construed as specification limits.