

Technical Data Sheet

# RONFALIN<sup>®</sup> ABS 1510 GF 30

Acrylonitrile Butadiene Styrene  
Engineering Plastics

**Product Description**

30% glass fiber reinforced ABS for injection molding of parts in structural applications. (Former name: RONFALIN 100G30)

**General**

- |                        |                                     |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight |
| Processing Method      | • Injection Molding                 |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.24 g/cm <sup>3</sup>	1.24 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	4.00 cm <sup>3</sup> /10min	4.00 cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.30 %	0.30 %	
Flow	0.10 %	0.10 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.02E+6 psi	7000 MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	11600 psi	80.0 MPa	ISO 527-2
Tensile Strain (Break)	2.5 %	2.5 %	ISO 527-2/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.4 ft·lb/in <sup>2</sup>	5.0 kJ/m <sup>2</sup>	ISO 179

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/Af
264 psi (1.8 MPa), Unannealed	203 °F	95.0 °C	
Vicat Softening Temperature	221 °F	105 °C	ISO 306/B50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·cm	> 1.0E+13 ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

**Additional Information**

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

**RONFALIN<sup>®</sup> ABS 1510 GF 30**

Acrylonitrile Butadiene Styrene  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Regrind	30 %	30 %
Processing (Melt) Temp	446 to 500 °F	230 to 260 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

**Notes**

These are typical property values not to be construed as specification limits.