

Technical Data Sheet

Ronfalin RXG03

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Uses	• Camera Applications		
RoHS Compliance	• RoHS Compliant		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm ³	1.20 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 Kg)	8.0 g/10 min	8.0 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Flexural Modulus	537000 psi	3700 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength	4.8 ft·lb/in ²	10 kJ/m ²	ISO 180/1A
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness	15700 psi	108 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	194 °F	90.0 °C	ISO 75-2/A
Vicat Softening Temperature	230 °F	110 °C	ISO 306/B50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Electric Strength	> 890 V/mil	> 35 kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	> 600 V	> 600 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.6 Mm))	HB	HB	UL 94

Notes

These are typical property values not to be construed as specification limits.