

Technical Data Sheet

Diamond Asa S170

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics

General		
Features	<ul style="list-style-type: none"> • Good Weather Resistance • High Impact Resistance 	
Agency Ratings	<ul style="list-style-type: none"> • EC 1907/2006 (REACH) • EU 2002/96/EC (WEEE) 	
RoHS Compliance	<ul style="list-style-type: none"> • RoHS Compliant 	
Forms	<ul style="list-style-type: none"> • Pellets 	
Processing Method	<ul style="list-style-type: none"> • Injection Molding 	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.06	1.06 g/cm ³	ASTM D792
73°F (23°C)	1.06 g/cm ³	1.06 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238 ISO 1133
220°C/10.0 Kg	12 g/10 min	12 g/10 min	
230°C/3.8 Kg	2.4 g/10 min	2.4 g/10 min	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength - Flow			
Yield, 73°F (23°C), Injection Molded ¹	5930 psi	40.9 MPa	ASTM D638
Yield, Injection Molded	5770 psi	39.8 MPa	ISO 527-2/50
Flexural Modulus - Chord, Flow			
73°F (23°C), Injection Molded	291000 psi	2010 MPa	ASTM D790
73°F (23°C), Injection Molded	297000 psi	2050 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F (-30°C), Injection Molded	4.8 ft·lb/in ²	10 kJ/m ²	
73°F (23°C), Injection Molded	12 ft·lb/in ²	25 kJ/m ²	
Notched Izod Impact			
Flow : -22°F (-30°C), Injection Molded	2.4 ft·lb/in	130 J/m	ASTM D256
Flow : 73°F (23°C), Injection Molded	7.5 ft·lb/in	400 J/m	ASTM D256
-22°F (-30°C), Injection Molded	3.9 ft·lb/in ²	8.3 kJ/m ²	ISO 180
73°F (23°C), Injection Molded	15 ft·lb/in ²	31 kJ/m ²	ISO 180

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			
R-scale, Injection Molded	91	91	ASTM D785
R-scale, 73°F (23°C)	95	95	ISO 2039-2

Technical Data Sheet

Diamond Asa S170

Acrylonitrile Styrene Acrylate
 LyondellBasell Industries
 Engineering Plastics

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed, 0.125 In (3.18 Mm), Injection Molded	191 °F	88.6 °C	ASTM D648
66 Psi (0.45 Mpa), Unannealed	191 °F	88.5 °C	ISO 75-2/B
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm), Injection Molded	168 °F	75.7 °C	ASTM D648
264 Psi (1.8 Mpa), Unannealed	168 °F	75.3 °C	ISO 75-2/A
Vicat Softening Temperature			
--	215 °F	102 °C	ASTM D1525
--	216 °F	102 °C	ISO 306
CLTE			
Flow : -22 To 176°f (-30 To 80°c)	4.7E-5 in/in/°F	8.4E-5 cm/cm/°C	ISO 11359-2
Transverse : -22 To 176°f (-30 To 80°c)	5.6E-5 in/in/°F	1.0E-4 cm/cm/°C	

Technical Data Sheet

Diamond Asa S170

Acrylonitrile Styrene Acrylate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Suggested Shot Size	40 to 70 %	40 to 70 %
Rear Temperature	446 to 500 °F	230 to 260 °C
Middle Temperature	450 to 509 °F	232 to 265 °C
Front Temperature	455 to 522 °F	235 to 272 °C
Nozzle Temperature	428 to 522 °F	220 to 272 °C
Processing (Melt) Temp	428 to 522 °F	220 to 272 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Rate	Fast	Fast
Back Pressure	75.0 to 150 psi	0.517 to 1.03 MPa

Notes

¹ 2.0 in/min (50 mm/min)

Notes

These are typical property values not to be construed as specification limits.