

Technical Data Sheet

Polyman ASA WR/MI E UV LM RED57355

Acrylonitrile Styrene Acrylate

Product Description

medium impact ASA grade with good weatherability

Processing Method Injection Molding**Resin ID** ASA

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	19	cm ³ /10 min	ISO 1133
Density, (Method A)	1.05	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	39.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.1	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	1800	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	17	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	5.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	80	kJ/m ²	ISO 179
Hardness			
Ball Indentation Hardness, (H 358/30)	82.0	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	93.0	°C	ISO 306
(A (10N), 50 °C/h)	102	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	82.0	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	71.0	°C	ISO 75-2/A
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	600	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			

Glow Wire Flammability Index			
(1.5 mm)	675 °C		IEC 60695-2-12
(3.0 mm)	675 °C		IEC 60695-2-12
Glow Wire Ignition Temperature			
(1.5 mm)	700 °C		IEC 60695-2-13
(3.0 mm)	700 °C		IEC 60695-2-13
UL Information			
Flammability Classification			
(1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20
UL File Number	E86615		