

Technical Data Sheet

Schulblend M/MW SFUV 5Z NAT



Acrylonitrile Styrene Acrylate + PA

Product Description

ASA/PA blend with high light stability and heat resistance

Processing Method Injection Molding

Attribute Good Flow; Good Impact Resistance; High Heat Resistance; UV Resistant

Additive UV Stabilizer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (250 °C/5.0 kg)	15	cm ³ /10 min	ISO 1133
Density, (Method A)	1.12	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	55.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	4.0	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2000	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	15	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	5.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	77	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	142	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	116	°C	ISO 75-2/B
Flammable			
Burning Rate, (2.00 mm)	<100	mm/min	ISO 3795
UL Information			
Flammability Classification, (1.6 mm)	HB		IEC 60695-11-10, -20

Injection Parameters	Nominal Value	Units
Drying Time	4	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	230 to 270	°C
Mold Temperature	40 to 80	°C