

Technical Data Sheet

Microthene FE53200

Ethylene Vinyl Acetate

Product Description

Microthene F polyolefin powders are ultra-fine, spherically shaped particles with narrow size distribution suitable for use in a broad range of specialty applications. *Microthene* F powders combine the unique properties of a polyolefin resin with a microfine particle size.

Application Automotive Parts; Colour Concentrates; Industrial; Interior Automotive Applications; Structural Parts

Market Consumer Products; Flexible Packaging; Healthcare; Industrial, Building & Construction

Processing Method Powders

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Equivalent Melt Index	8.0	g/10 min	8.0	g/10 min	ASTM D1238
Density, (23 °C)	0.926	g/cm ³	0.926	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus	13500	psi	93.1	MPa	ASTM D790
Tensile Strength at Break	1700	psi	11.7	MPa	ASTM D638
Tensile Elongation at Break	675	%	675	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	38		38		ASTM D2240
Thermal					
Vicat Softening Point	167.0	°F	75.0	°C	ASTM D1525
Low Temperature Brittleness	<-105	°F	<-76	°C	ASTM D746
Peak Melting Point	204.8	°F	96.0	°C	ASTM D3418
Additional Information					
Particle Shape	Spherical		Spherical		LYB Method
Average Particle Size	20	micron	20	micron	LYB Method
Particle Size Distribution	5 - 50	micron	5 - 50	micron	LYB Method
Moisture Content	<=0.1	%	<=0.1	%	LYB Method