

Technical Data Sheet

Alathon L4904LSC



High Density Polyethylene

Product Description

Alathon L4904LSC is a bimodal, high molecular weight, high density polyethylene resin with excellent processing characteristics. L4904LSC is selected by customers for pressure pipe applications including industrial piping, mining, oil & gas gathering, municipal water service lines and sewers. Customers typically use L4904LSC in large diameter, thick wall applications requiring high resistance to pipe failure by rapid crack propagation and slow crack growth mechanisms. When L4904LSC is combined with a LyondellBasell approved color or black masterbatch at the correct use level, this compound may meet the following standards or requirements:

- ASTM D3350 Cell Classifications: **PE445574C**. For Oxidative Resistance Classification Categorization values (CC) please contact your LyondellBasell Technical Service Engineer or Sales Manager.
- NSF Standard 14 and Standard 61 for Potable Water Pipe and Fittings
- Plastic Pipe Institute (PPI) PE4710 per PPI TR-3, PE 100 Cell Classification: **PE445576C**

Application	Drainage Pipe; Drinking Water Pipe; Industrial; Soil & Waste Pipe
Market	Industrial, Building & Construction; Pipe
Processing Method	Pipe

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate					
(190 °C/5.0 kg)	0.15	g/10 min	0.15	g/10 min	ASTM D1238
(190 °C/21.6 kg)	7	g/10 min	7	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm ³	0.949	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (2% Secant)	137000	psi	945	MPa	ASTM D790
Tensile Stress at Break	4640	psi	32	MPa	ASTM D638
Tensile Stress at Yield	3500	psi	24	MPa	ASTM D638
Tensile Elongation at Break	520	%	520	%	ASTM D638
PENT on Natural Resin, (2.4 MPa, 80 °C, Air)	5000	hr	5000	hr	ASTM F1473
Thermal					
Low Temperature Brittleness, F ₅₀	<-96	°F	<-71	°C	ASTM D746
DSC Induction Temperature	527	°F	275	°C	ASTM D3350
Oxidative-Induction Time, (200 °C)	>110	min	>110	min	ASTM D3895
Conformance Testing					
Hydrostatic Design Basis					
(73 °F)	1600	psi			ASTM D2837
(140 °F)	1000	psi			ASTM D2837
Minimum Required Strength, (20 °C)			10	MPa	ISO 9080