

Technical Data Sheet

**Alathon L5885**



High Density Polyethylene

**Product Description**

Alathon L5885 is a medium molecular weight high density polyethylene homopolymer for use in blown film applications. Typical applications include those with low WVTR requirements.

<b>Application</b>	Bags & Pouches; Barrier Film; Food Packaging Film; Lamination Film
<b>Market</b>	Flexible Packaging
<b>Processing Method</b>	Blown Film
<b>Attribute</b>	Barrier Resin; General Purpose; Good Organoleptic Properties; High Density; Low Gel; Moisture Barrier

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	0.85	g/10 min	0.85	g/10 min	ASTM D1238
Density, (23 °C)	0.958	g/cm <sup>3</sup>	0.958	g/cm <sup>3</sup>	ASTM D1505
<b>Film</b>					
Tensile Strength at Break					
MD	7900	psi	54.5	MPa	ASTM D882
TD	3400	psi	23.4	MPa	ASTM D882
Tensile Strength at Yield					
MD	3700	psi	25.5	MPa	ASTM D882
TD	3800	psi	26.2	MPa	ASTM D882
Tensile Elongation at Break					
MD	700	%	700	%	ASTM D882
TD	750	%	750	%	ASTM D882
Secant Modulus					
MD	136000	psi	938	MPa	ASTM D882
TD	184000	psi	1270	MPa	ASTM D882
Elmendorf Tear Strength					
MD	30	g	30	g	ASTM D1922
TD	900	g	900	g	ASTM D1922