

Technical Data Sheet

Alathon M5265

High Density Polyethylene

Product Description

Alathon M5265 is a narrow molecular weight distribution octene-copolymer used in the manufacture of open-head pails and covers.

Regulatory Status

For regulatory compliance information, see Alathon M5265 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Containers; Pails
Market	Rigid Packaging
Processing Method	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	6.5	g/10 min	6.5	g/10 min	ASTM D1238
Density, (23 °C)	0.9515	g/cm ³	0.9515	g/cm ³	ASTM D1505
Bulk Density	37-39	lb/ft ³	593-625	kg/m ³	ASTM D1895
Spiral Flow	7.7	in	19.6	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	164000	psi	1130	MPa	ASTM D790
(2% Secant)	137000	psi	945	MPa	ASTM D790
Flexural Young's Modulus	188000	psi	1300	MPa	ASTM D790
Tensile Modulus, (1% Secant)	98800	psi	681	MPa	ASTM D638
Tensile Young's Modulus	111000	psi	765	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	>4010	psi	>27.6	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	3830	psi	26.4	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	>2230	%	>2230	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	12	%	12	%	ASTM D638
Impact					
Notched Izod Impact Strength, (23 °C)	1.2	ft-lb/in	64	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
Hardness					
Shore Hardness, (Shore D, max)	71		71		ASTM D2240
Thermal					
Vicat Softening Temperature	261	°F	127	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	157	°F	69.4	°C	ASTM D648
Melting Temperature	269.1	°F	131.7	°C	ASTM D3418
Crystallization Temperature	244.0	°F	117.8	°C	ASTM D3418

Notes

Conditions of Tensile Stress and Elongation values are: 50 mm/min, Type IV specimen.

Conditions of Flexural Modulus values are: 0.5 inches/min or 12.5 mm/min.

Conditions of Tensile Modulus values are: 50 mm/min, Type I Specimen.

Tensile Stress and Elongation @ Break Specimens failed to break within testing limits.

Spiral Flow measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.0625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440 °F.

Deflection Temperature Under Load and Low Temperature Brittleness data are for control and development work and are not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.