

Technical Data Sheet

Alathon M5370



High Density Polyethylene

Product Description

Alathon M5370 is a copolymer with a narrow molecular weight distribution. This resin provides high impact strength, excellent color, low odor and good processing stability. Typical applications include open head pails and large shipping containers.

Regulatory Status

For regulatory compliance information, see Alathon M5370 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Containers; Pails
Market	Rigid Packaging
Processing Method	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	6.9	g/10 min	6.9	g/10 min	ASTM D1238
Density, (23 °C)	0.953	g/cm ³	0.953	g/cm ³	ASTM D1505
Bulk Density	33-37	lb/ft ³	529-593	kg/m ³	ASTM D1895
Spiral Flow	8.9	in	22.6	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	189000	psi	1300	MPa	ASTM D790
(2% Secant)	158000	psi	1090	MPa	ASTM D790
Flexural Young's Modulus	205000	psi	1410	MPa	ASTM D790
Tensile Modulus, (1% Secant)	119000	psi	820	MPa	ASTM D638
Tensile Young's Modulus	151000	psi	1040	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	2990	psi	20.6	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4130	psi	28.5	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	1150	%	1150	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	9	%	9	%	ASTM D638
Impact					
Notched Izod Impact Strength, (23 °C)	0.73	ft-lb/in	39	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
Hardness					
Shore Hardness, (Shore D, max)	71		71		ASTM D2240
Thermal					
Vicat Softening Temperature	261	°F	127	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746

Deflection Temperature Under Load, (66 psi, Unannealed)	162 °F	72 °C	ASTM D648
Melting Temperature	266.5 °F	130.3 °C	ASTM D3418
Crystallization Temperature	241.7 °F	116.5 °C	ASTM D3418

Notes

Conditions of Tensile Stress and Elongation values are: 50 mm/min, Type IV specimen.

Conditions of Flexural Modulus values are: 0.5 inches/min or 12.5 mm/min.

Conditions of Tensile Modulus values are: 50 mm/min, Type I Specimen.

Spiral Flow measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.0625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440 °F.

Deflection Temperature Under Load and Low Temperature Brittleness data are for control and development work and are not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

These are typical property values not to be construed as specification limits.