

Technical Data Sheet

Alathon M5370

High Density Polyethylene

Product Description

Alathon M5370 is a copolymer with a narrow molecular weight distribution. This resin provides high impact strength, excellent color, low odor and good processing stability. Typical applications include open head pails and large shipping containers.

Application	Containers; Pails
Market	Rigid Packaging
Processing Method	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	6.9	g/10 min	6.9	g/10 min	ASTM D1238
Density, (23 °C)	0.953	g/cm ³	0.953	g/cm ³	ASTM D1505
Bulk Density	33-37	lb/ft ³	529-593	kg/m ³	ASTM D1895
Spiral Flow	8.9	in	22.6	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	189000	psi	1300	MPa	ASTM D790
(2% Secant)	158000	psi	1090	MPa	ASTM D790
Flexural Young's Modulus	205000	psi	1410	MPa	ASTM D790
Tensile Modulus, (1% Secant)	119000	psi	820	MPa	ASTM D638
Tensile Young's Modulus	151000	psi	1040	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	2990	psi	20.6	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4130	psi	28.5	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	1150	%	1150	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	9	%	9	%	ASTM D638
Impact					
Notched Izod Impact Strength, (23 °C)	0.73	ft-lb/in	39	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
Hardness					
Shore Hardness, (Shore D, max)	71		71		ASTM D2240
Thermal					
Vicat Softening Temperature	261	°F	127	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	162	°F	72	°C	ASTM D648
Melting Temperature	266.5	°F	130.3	°C	ASTM D3418
Crystallization Temperature	241.7	°F	116.5	°C	ASTM D3418