

## Technical Data Sheet

**Alathon M6028**

High Density Polyethylene

**Product Description**

Alathon M6028 is a homopolymer that is warp resistant, exhibits excellent toughness, stiffness and color as well as low odor and good processing stability. Typical applications include hardware items and heavy wall moldings.

<b>Application</b>	Industrial
<b>Market</b>	Rigid Packaging
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	2.8	g/10 min	2.8	g/10 min	ASTM D1238
Density, (23 °C)	0.958	g/cm <sup>3</sup>	0.958	g/cm <sup>3</sup>	ASTM D1505
Bulk Density	37-39	lb/ft <sup>3</sup>	593-625	kg/m <sup>3</sup>	ASTM D1895
Spiral Flow	6.4	in	16.3	cm	LYB Method
<b>Mechanical</b>					
Flexural Modulus					
(1% Secant)	186000	psi	1280	MPa	ASTM D790
(2% Secant)	153000	psi	1050	MPa	ASTM D790
Flexural Young's Modulus	203000	psi	1400	MPa	ASTM D790
Tensile Modulus, (1% Secant)	116000	psi	800	MPa	ASTM D638
Tensile Young's Modulus	137000	psi	945	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	4510	psi	31.1	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4120	psi	28.4	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	>1000	%	>1000	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	10	%	10	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength, (23 °C)	2.68	ft-lb/in	143	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
<b>Hardness</b>					
Shore Hardness, (Shore D, max)	71		71		ASTM D2240
<b>Thermal</b>					
Vicat Softening Temperature	264	°F	129	°C	ASTM D1525
Low Temperature Brittleness, F <sub>50</sub>	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	167	°F	75	°C	ASTM D648
Melting Temperature	271.0	°F	132.8	°C	ASTM D3418
Crystallization Temperature	240.8	°F	116.0	°C	ASTM D3418