

## Technical Data Sheet

### *Alathon M6080*



High Density Polyethylene

#### Product Description

*Alathon M6080* is a narrow molecular weight distribution homopolymer that exhibits enhanced flow characteristics and good balance of stiffness and impact resistance. Typical applications include cases, tote bins, crates and trays and open-head pails.

**Application** Crates; Pallets/Trays/Tote Bins

**Market** Rigid Packaging

**Processing Method** Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	7.9	g/10 min	7.9	g/10 min	ASTM D1238
Density, (23 °C)	0.960	g/cm <sup>3</sup>	0.960	g/cm <sup>3</sup>	ASTM D1505
Bulk Density	37-39	lb/ft <sup>3</sup>	593-625	kg/m <sup>3</sup>	ASTM D1895
Spiral Flow	8.6	in	21.8	cm	LYB Method
<b>Mechanical</b>					
Flexural Modulus					
(1% Secant)	190000	psi	1310	MPa	ASTM D790
(2% Secant)	155000	psi	1070	MPa	ASTM D790
Flexural Young's Modulus	205000	psi	1410	MPa	ASTM D790
Tensile Modulus, (1% Secant)	123000	psi	848	MPa	ASTM D638
Tensile Young's Modulus	146000	psi	1010	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	2300	psi	15.9	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4250	psi	29.3	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	380	%	380	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	11	%	11	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength, (23 °C)	1.4	ft-lb/in	75	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
<b>Hardness</b>					
Shore Hardness, (Shore D, max)	70		70		ASTM D2240
<b>Thermal</b>					
Vicat Softening Temperature	264	°F	129	°C	ASTM D1525
Low Temperature Brittleness, F <sub>50</sub>	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	176	°F	80	°C	ASTM D648
Melting Temperature	270.9	°F	132.7	°C	ASTM D3418
Crystallization Temperature	240.6	°F	115.9	°C	ASTM D3418