

Technical Data Sheet

Hyperzone HY54907U



High Density Polyethylene

Product Description

Hyperzone HY54907U is a high density polyethylene resin that exhibits excellent processability, outstanding environmental stress crack resistance and stiffness. Typical applications include intermediate bulk containers (IBC), jerry cans, and heating oil tanks.

Application	Industrial Packaging; Intermediate Bulk Containers
Market	Rigid Packaging
Processing Method	Extrusion Blow Molding
Attribute	Excellent ESCR (Environmental Stress Cracking Resistance); Excellent Processability; UV Stabilized

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/21.6 kg)	7.5	g/10 min	7.5	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm ³	0.949	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus, (1% Secant)	170000	psi	1170	MPa	ASTM D790
Tensile Strength at Yield	3400	psi	23.4	MPa	ASTM D638
Environmental Stress Crack Resistance, F ₅₀ (100% Igepal®, Cond B)	>3000	hr	>3000	hr	ASTM D1693
FNCT, (4.0 MPa, 2% Arkopal N100, 80 °C)	1100	hr	1100	hr	ISO 16770
Impact					
Tensile Impact Strength	>600	ft-lb/in ²	>1260	kJ/m ²	ASTM D1822
Hardness					
Shore Hardness, (Shore D)	68		68		ASTM D2240
Thermal					
Vicat Softening Temperature	261	°F	127	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	150	°F	66	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.