

Technical Data Sheet**Hostalen 23050 B**

High Density Polyethylene

Product Description

Hostalen 23050 B is a high density polyethylene (HDPE) in nature color, with high melt viscosity for extrusion, injection and compression molding. It is not applicable for pressurized pipe application.

This grade is not intended for medical and pharmaceutical applications.

| | |
|--------------------------|--|
| Application | Conduit; Drainage Pipe; Sewer Pipe |
| Market | Industrial, Building & Construction; Pipe |
| Processing Method | Compression Molding; Pipe; Sheet |
| Attribute | Good Abrasion Resistance; Good Chemical Resistance; High Density; High Viscosity; Weldable |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate | | | |
| (190 °C/5.0 kg) | 0.23 | g/10 min | ISO 1133-1 |
| (190 °C/21.6 kg) | 6.4 | g/10 min | ISO 1133-1 |
| Density | 0.950 | g/cm ³ | ISO 1183-1 |
| Mechanical | | | |
| Tensile Modulus, (23 °C) | 900 | MPa | ISO 527-1, -2 |
| Tensile Stress at Yield, (23 °C, 50 mm/min) | 24 | MPa | ISO 527-1, -2 |
| Tensile Strain at Break, (23 °C) | >500 | % | ISO 527-1, -2 |
| Impact | | | |
| Charpy Impact Strength - Notched, (23 °C) | 20 | kJ/m ² | ISO 179-1/1eA |
| Thermal | | | |
| Oxidation Induction Time, (210 °C) | >25 | min | ISO 11357-6 |
| Additional Information | | | |
| Moisture Content | <=0.02 | % | LYB Method |

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Further Information

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.