

## Technical Data Sheet

### *Icorene* 5760 GRN 6149



High Density Polyethylene

#### Product Description

*Icorene* 5760 is a high density polyethylene specifically developed for rotational moulding. This grade is particularly suitable for use in kayaks and boat applications. It has very high stiffness and scratch resistance combined with good processability.

<b>Processing Method</b>	Rotomolding
<b>Attribute</b>	Good Processability; High Scratch Resistance; Ultra High Stiffness; UV Resistant
<b>Forms</b>	Powder
<b>Appearance</b>	Natural Color; Unspecified Color
<b>Additive</b>	UV Stabilizer
<b>Application</b>	Water Sports Equipment

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (190 °C/2.16 kg)	3.5	g/10 min	ASTM D1238
Density	0.949	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>			
Tensile Strength at Yield	23	MPa	ASTM D638
Environmental Stress Crack Resistance, (10% Igepal, 50 °C)	45.0	hr	ASTM D1693
Flexural Modulus	1020	MPa	ASTM D790
<b>Impact</b>			
Charpy Impact Strength - Notched	12	kJ/m <sup>2</sup>	ISO 179
Drop Impact Resistance, (-20 °C, Internal Method)	205	J/cm	ASTM D4226

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.