

LyondellBasell Petrothene® LB5003 High Density Polyethylene (Unverified Data)**

Categories: [Polymer](#); [Thermoplastic](#); [Polyethylene \(PE\)](#); [High Density \(HDPE\)](#); [High Density Polyethylene \(HDPE\)](#), [Blow Molding Grade](#)

Material Notes:

Applications
The PETROTHENE LB 5003 series of polyethylene resins exhibits excellent environmental stress crack resistance and is especially designed for heavy duty bottles, such as those containing detergent and chemicals.

Regulatory Status
The base resin LB 5003 meets the requirements of Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply.

Processing Techniques
Specific recommendations for processing LB 5003 can only be made when the processing conditions, equipment and end use are known.

This product is from the former Equistar product line.

Vendors: No vendors are listed for this material. Please [click here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Density	0.949 g/cc	0.0343 lb/in ³	ASTM D1505
Environmental Stress Crack Resistance	75 hour	75 hour	F ₅₀ ; ASTM D1693
ESCR, Bottle	>= 500 hour	>= 500 hour	F ₅₀ ; ASTM D2561
Melt Flow	0.30 g/10 min	0.30 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength, Yield	26.2 MPa	3800 psi	ASTM D638
Elongation at Break	>= 600 %	>= 600 %	ASTM D638
Flexural Modulus	1.17 GPa	170 ksi	ASTM D790
Tensile Impact	64.1 J/cm	120 ft-lb/in	ASTM D1822

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	72.0 °C	162 °F	ASTM D648
Vicat Softening Point	122 °C	252 °F	ASTM D1525
Brittleness Temperature	<= -76.0 °C	<= -105 °F	F ₅₀ ; ASTM D746

**
This data sheet is not an active part of MatWeb and the information on it should not be considered reliable. Inactive data sheets have usually been replaced with newer information on the same material. If this is the case, you can find the active data sheet by using any of our search tools, including the Quick Search box in the upper part of this page. If you are unable to locate an active data sheet for this material, then this material is likely discontinued, although various other reasons may be behind its removal. In any event, do not rely on the information on this page to be accurate or maintained. You may have reached this data sheet through an outdated bookmark or link. Please update your bookmark accordingly. We apologize if you have accessed this page through MatWeb's usual search tools.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's [terms of use](#) regarding this information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.